

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 723 561 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
10.12.1997 Bulletin 1997/50

(51) Int Cl.⁶: **C08G 18/50, C08L 97/02**

(21) Application number: **94928898.9**

(86) International application number:
PCT/EP94/03371

(22) Date of filing: **13.10.1994**

(87) International publication number:
WO 95/10555 (20.04.1995 Gazette 1995/17)

(54) MOISTURE-ACTIVATED ADHESIVE COMPOSITIONS

FEUCHTIGKEITSAKTIVIERBARE KLEBSTOFFZUSAMMENSETZUNGEN
COMPOSITIONS ADHESIVES ACTIVEES PAR L'HUMIDITE

(84) Designated Contracting States:
BE DE ES FR GB IT NL

• **YAVORSKY, James, Anthony**
Mickleton, NJ 08056 (US)

(30) Priority: **14.10.1993 US 136359**

(74) Representative: **Swinnen, Anne-Marie**
ICI EUROPE Ltd.,
ICI POLYURETHANES,
Intellectual Property Department,
Everslaan 45
3078 Everberg (BE)

(43) Date of publication of application:
31.07.1996 Bulletin 1996/31

(73) Proprietor: **IMPERIAL CHEMICAL INDUSTRIES**
PLC
London SW1P 3JF (GB)

(56) References cited:
EP-A- 0 012 927 **EP-A- 0 352 558**
EP-A- 0 527 568 **DE-A- 1 922 626**

(72) Inventors:
• **ROBERTSON, John, Russel**
Glen Mills, PA 19342 (US)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 723 561 B1

DescriptionField of the Invention

5 The present invention is directed to moisture-activated adhesive compositions and methods for their production and a process for bonding multiple substrates using said composition. More specifically, the present invention is directed to moisture-activated adhesive compositions which are cold curable.

Background of the Invention

10 Adhesives suitable for use in wood products which demonstrate a prolonged pot life and a fast cure rate have long been desirable. Such adhesives would be useful in the manufacture of plywood, chip board, fiberboard, etc. However, these characteristics have proven to be difficult to obtain in simple formulations.

15 The plywood industry also has a need for adhesives which can effectively bond lignocellulosic solutions having a relatively high moisture content to effectively produce laminated veneers. For example, it would be desirable for adhesives used in these industries to be able to bond substrates having a moisture content of, e.g., 10% to 20%. Most conventional adhesives, such as those of the phenol-formaldehyde type, require a moisture content below 7%.

20 Examples of such phenol-formaldehyde type resins are disclosed, e.g., in Plywood and Adhesive Technology, Sellers, Jr., Marcel Dekker, Inc. (1985). These resins provide excellent adhesion, but are disadvantageous in that they require heat activation and a considerable amount of time to cure. Moreover, as noted above, such resins cannot be used effectively with substrates having high moisture levels. Thus, the substrates must be dried to a relatively low moisture content (generally about 5% by weight) resulting in a loss of wood volume and an increase in the cost and time of production.

25 Isocyanate-based adhesives are also known and have been employed in the preparation of laminated wood and paper structures. Polyisocyanates have been used as adhesives in the formation of waferboard, fiberboard and paper laminates from cellulose and lignocellulosic materials. An example of an isocyanate based adhesive is set forth in U. S. Patent No. 4,414,361 which discloses polyisocyanate-cyclic alkaline carbonate binder compositions and their use in the preparation of lignocellulosic composite molded products. This patent discloses the addition of the adhesive to lignocellulosic material and molding this mixture at temperatures of from about 140°C to 220°C. These polyisocyanates 30 require temperatures of up to 200°C or more for curing in order to develop acceptable physical bonding strengths. The use of such extreme temperatures reduces wood volume and is often not desirable from a cost or processing standpoint. DE-A-1922626 describes moisture-activated adhesive compositions of a polyisocyanate and an isocyanate-reactive component, the latter being a polyether alcohol with at least one tertiary N-atom and preferably at least 3-hydroxyl groups.

35 Accordingly, it can be seen that there is a need for one component adhesive compositions useful in the preparation of lumber replacements, such as laminated veneer lumber, which fully cure at relatively low temperatures, e.g., room temperature. There is also a need for such adhesives which have a prolonged pot life suitable for use in commercial production methods. Moreover, there is a need for processes for preparing composite products with cellulosic and lignocellulosic materials using such adhesives.

Summary of the Invention

45 These objectives are obtained by the present adhesive compositions which demonstrate excellent adhesive properties with a prolonged pot life and fast cure, particularly at room temperature. The present compositions are activated by the moisture present in the substrate with which they are being used and thus, they may be most effectively used with substrates having a relatively high moisture content, such as 7% or more. Accordingly, the present compositions are effectively used with various types of lignocellulosic materials and are particularly useful in the preparation of lumber replacements as discussed above. The present adhesive compositions have a further advantage over prior art systems in that they are cold curable, i.e., may be cured at room temperature, or by the application of heat.

50 The present invention is directed to moisture-activated adhesive compositions comprising the reaction product of (a) 99 to 70% a polyisocyanate and (b) 1 to 30 % by weight of an isocyanate-reactive component comprising at least one aliphatic tertiary amine group containing polyol made by alkoxylation of amines or aminoalcohols with at least two active hydrogen atoms with ethylene oxide and optionally propylene oxide, having an ethylene oxide content of at least 1% and a concentration of nitrogen of 0.002 to 0.02 eqN/100g. The present invention is further directed to a process 55 for bonding multiple substrates comprising: (1) applying to a surface of a first substrate a moisture-activated adhesive composition as defined above comprising the reaction product of (a) a polyisocyanate and (b) an isocyanate-reactive component comprising at least one aliphatic tertiary amine group-containing polyol having an ethylene oxide content of at least 1%; (2) contacting this surface of the substrate with a surface of a second substrate; (3) applying pressure

to the contacted surfaces; and (4) curing the adhesive composition.

Detailed Description of the Invention

5 The present adhesive compositions comprise 99 to 70%, preferably 93 to 80% and most preferably 90 to 80% by weight of the polyisocyanate component.

Polyisocyanates useful in the present invention are those having a number-average isocyanate functionality of 2.0 or greater, preferably greater than 2.1, more preferably greater than 2.3 and most preferably greater than 2.5. Useful polyisocyanates should have a number average molecular weight of from 100 to 5000 and preferably 120 to 1800. Preferably, at least 50 mole percent and preferably at least 90 mole percent of the isocyanate groups are bonded directly to aromatic groups.

Suitable aromatic polyisocyanates include, e.g., p-phenylene diisocyanate; m-phenylene diisocyanate; 2,4-toluene diisocyanate; 2,6-toluene diisocyanate; naphthalene diisocyanate; dianisidine diisocyanate; polymethylene polyphenyl polyisocyanate; 2,4'-diphenyl methane diisocyanate (2,4'-MDI); 4,4'-diphenylmethane diisocyanate (4,4'-MDI); 3,3'-dimethyl-4,4'-biphenylene diisocyanate; polydiphenylmethane polyisocyanate having a functionality of greater than 2; and mixtures thereof. The polyisocyanates should have a 2,4'-MDI content of less than 18.0%, preferably less than 10% and most preferably less than 5%. The MDI isomers, mixtures of these isomers with polydiphenylmethane polyisocyanates, polydiphenylmethane itself and derivatives thereof are preferred.

The polyisocyanate may include minor amounts of aliphatic polyisocyanates. Suitable aliphatic polyisocyanates include isophorone diisocyanate; 1,6-hexamethylene diisocyanate; 1,4-cyclohexyl diisocyanate; saturated analogues of the above-mentioned aromatic polyisocyanates and mixtures thereof.

The polyisocyanate component of the present composition is preferably a polymeric polyisocyanate, and more preferably a polymeric diphenylmethane diisocyanate. Commercially available polymeric polyisocyanates include Rubiflex® 26A available from ICI Americas Inc., Wilmington, Delaware.

Isocyanate-terminated prepolymers may also be employed in the present invention. As used herein, the term "isocyanate-terminated prepolymer" includes the prepolymer as well as the pseudoprepolymer, i.e., a mixture of the prepolymer and the polyisocyanate from which the prepolymer is prepared. The isocyanate-terminated prepolymer useful in the present compositions should have a free isocyanate (NCO) content of from 10 to 26%, preferably 16 to 26%. In general, the polymeric polyisocyanate may be prepared by the reaction of an excess of a polyisocyanate and a polyol, including aminated polyols or imino/enamines thereof.

Suitable polyols for preparing the isocyanate-terminated prepolymers include:

- (a) polyether polyols, thioether polyols and/or hydrocarbon-based polyols having a molecular weight of from 1000 to 3000 and an average hydroxyl functionality of from 1.9 to 4;
- (b) polyester polyols having a molecular weight of 1000 or more and an average hydroxyl functionality of from 1.9 to 4.

A particularly preferred isocyanate-terminated prepolymer useful in the present invention are MDI prepolymers which are the reaction product of an excess of polymeric MDI and polyether polyols. The polyether polyols are preferably diols or triols having hydroxy values of 25 to 120. The polyol should have a number average molecular weight in the range of 1000 to 3000. Such prepolymers should generally have a free-NCO content of more than 10%, preferably more than 16% and most preferably 16 to 26%. Suitable polymers are those in which the stoichiometric ratio of isocyanate (NCO) to hydroxyl (OH) exceeds 1:1. Rubinate® M available from ICI Americas is a suitable polymeric MDI composition useful in the present invention.

Most preferably, the polyisocyanate component is a blend of polymeric MDI, such as the aforementioned Rubinate® M and pure MDI. Such blends have been found to provide improved penetration into the lignocellulosic substrate and higher wood failure as opposed to glue-line failure. A commercially available pure MDI product suitable for use in the present invention is Rubinate® available from ICI Americas Inc. These blends contain polymeric MDI to pure MDI in ratios of 95:5 to 50:50 and preferably 60:40 to 80:20.

The second component of the present compositions is an isocyanate-reactive component comprising at least one aliphatic tertiary amine group-containing polyol having an ethylene oxide content of at least 1%. Preferably, the ethylene oxide content is from 1 to 90%, preferably 5 to 60% and most preferably 10 to 40%. The aliphatic tertiary amine group-containing polyol provides an ethylene oxide content in the prepolymer of 0.01 to 27%, preferably 0.35 to 12% and most preferably 1 to 8%. This amount of ethylene oxide is the total amount in the prepolymer. It has been found that the polyol may contain any amount of propylene oxide.

The aliphatic tertiary amine group-containing polyols are the known alkoxylation products of amines or aminoalcohols with at least two active hydrogen atoms with ethylene oxide and optionally propylene oxide. Suitable initiator molecules include: ammonia, ethylene diamine, hexamethylene diamine, methyl amine, diaminodiphenyl methane,

aniline, ethanolamine, diethanolamine, N-methyl diethanolamine, and tetrahydroxyl ethyl ethylenediamine.

Suitable aliphatic tertiary amine group-containing polyols are those wherein the initiator comprises 1 to 18 and preferably 1 to 6 carbon atoms. Suitable aliphatic tertiary amine group-containing polyols have an average molecular weight of about 1500 to 10,000 and preferably 1500 to 6000 and an average OH functionality of 1.8 to 6.0.


The present inventors have found that the concentration of nitrogen in the amine group-containing polyol is related to the effectiveness, i.e., fast cure rate, of the composition. The nitrogen concentration is 0.002 to 0.02 eqN/100g, preferably 0.004 to 0.008 eqN/100g and most preferably 0.006 eqN/100g.

Preferred amine group-containing polyols for use in the present invention include those prepared from ethylene diamine, triethylene tetramine and triethanolamine.

The present compositions comprise component (b), the aliphatic tertiary amine group-containing polyol component, in an amount of 1 to 30%, preferably 7 to 20% and most preferably 10 to 20% by weight based upon the total amount of isocyanate and polyol in the composition.

In its most preferred form, the amine group-containing polyol is an ethylene diamine-based polyol containing ethylene oxide. Suitable ethylene diamine-based polyols are those having an ethylene oxide content of 1 to 90%, preferably 5 to 60%, and most preferably 10 to 40%. The ethylene oxide content refers to the amount of ethylene oxide utilized in the preparation of the polyols as discussed above. During production, the ethylene oxide reacts with the initiator. The polyols should have a molecular weight in the range of 1500 to 5000.

Suitable ethylene diamine-based polyols useful in the present compositions include those of the following formula:



wherein x is an integer of 1.0 to 29.0, preferably 4.0 to 20 and most preferably 4.0 to 14; and y is an integer of 0.1 to 10.0 and preferably 2.0 to 4.0. Suitable ethylene diamine-based polyols are available commercially, such as the "Syneronic T" series of polyols available from ICI Americas Inc.

Although not wishing to be limited to a single theory, it is believed that the amine group-containing polyol remains inactive in the present adhesive composition until it comes into contact with the moisture in the wood. Once the amine group-containing polyol contacts the moisture, it is believed to promote the reaction between the polyisocyanate and water in the system, thus accelerating adhesion. The result is that the present adhesives are relatively fast curing. Moreover, the adhesive remains on the surface of the wood where it is most effective and can develop the cold tack necessary for processing.

The present compositions may further comprise various compounds having a catalytic function to improve the cure rate of the system. Examples of appropriate catalysts are, e.g., the tertiary amine catalysts. Suitable tertiary amine catalysts are available commercially as Nix A-4 available from Union Carbide and Thancat DMDEE is available from Texaco. Most preferably, the Nix A-4 catalyst is used in the relatively slower cure systems.

When used in the present adhesive compositions, the catalysts are contained in an amount of from 0.1 to 2.0% parts by weight and preferably 0.25 to 1.0 parts by weight based on the weight of total amount of polyurethane in the compositions.

The present adhesive compositions may be prepared by simply mixing or blending the polyisocyanate component and the polyol component under suitable conditions, particularly if both components are liquids. No moisture should be allowed to enter the system. If one of the components is a solid, that component should be fully dissolved in the other liquid component. In any event, the components may be mixed or blended by any means evident to one skilled in the art from the present disclosure.

Conventional fillers, such as calcium carbonate, and clays are generally added to the composition. Fillers have been found useful to hold the adhesive on the surface of the substrate to be treated. Also, it may be necessary to utilize diluents and/or wetting agents to modify the viscosity of the composition. These materials are used in amounts appropriate for specific applications which will be evident to one skilled in the art based on the present disclosure.

The adhesive compositions of the present invention have been found to have a pot life of approximately one month or more under moisture-free conditions when mixed prior to application to a substrate.

The present compositions are also "cold curable", i.e., may be cured at a temperature of 10°C to room temperature although they can also be hot cured. Thus, the present compositions may be cured at temperatures of from 10°C to 250°C. Preferably the present compositions are cured at a temperature of 23°C to 125°C. Generally, most systems will cure at room temperature in 10-60 minutes.

The adhesive compositions of the present invention may be used to bond many different types of moisture-containing substrates. Preferably the present compositions are used to bond multiple wood substrates together to prepare engineering lumber products. It is preferred that at least one of the substrates be selected from the group consisting of wood, paper, rice hulls, cement, stone, cloth, grass, corn husks, bagasse, nut shells, polymeric foam films and sheets, polymeric foams and fibrous materials. Preferably, the present composition is used to fabricate multi-substrate composites or laminates, particularly those comprising lignocellulosic or cellulosic materials, such as wood or paper, to prepare products such as plywood, laminated veneer lumber, waterboard, particleboard, fiberboard, chipboard, and oriented wood products, such as "Parallam", available from McMillan Bloedel.

As the present adhesive compositions are moisture-activated, it is important that the substrates have a relatively high moisture content. Specifically, the substrates should have a moisture content of at least 7%. Preferably, the substrates have a moisture content of 10 to 20% by weight and more preferably 12 to 15% by weight.

When used to bond multiple substrates together, the present composition is applied to a surface of a first substrate. A surface of a second substrate is then contacted with the surface of the first substrate containing the present composition. Pressure is then applied to the contacted surfaces and the adhesive compositions are allowed to cure. The surface of the second substrate against which the first substrate is contacted is generally not coated with the present adhesive composition. However, that surface may also be coated prior to contacting the substrates.

The present adhesive compositions may also be formulated to provide cold tack immediately after application to a substrate. This is particularly useful for pre-press operations where mechanical handling is often necessary. Cold tack may be accomplished by inclusion of 10-20% of a faster acting ethylenediamine-based polyol in the formulation. Generally, those polyols having a relatively high ethylene oxide content, i.e., greater than 25%, are considered to be faster acting.

The present adhesive compositions may be applied to the surfaces of the substrates in any conventional manner. For example, the surface may be coated with the composition by spraying, brushing, etc. Suitable means for applying the adhesive compositions to the surface of the substrate for a particular application will be evident to one skilled in the art from the present disclosure.

After the coated substrates are contacted with each other, pressure is applied thereto. The pressure should be sufficient to cause the surfaces to adhere to one another. Generally, the amount of pressure and the time period for which the pressure is applied are not limited and specific pressures and times will be evident to one skilled in the art from the present disclosure. However, it has been found preferable that a pressure of approximately 10 to 200 psi (equivalent to 69 to 1380 kPa) be applied for 10 to 20 minutes to cause appropriate adhesion for most substrates. Further processing can generally be conducted on the treated substrates in one hour.

The invention is now illustrated by the following examples which are not intended to limit the scope of the invention.

EXAMPLES

The following adhesive compositions were prepared in accordance with the present invention.

Example 1

Formulation A	Parts By Weight
MDI prepolymer	25.0
Polyol 1	10.0
Thancat DMDEE	0.1
Calcium Carbonate No. 7	10.0
Benzaldehyde	0.5

The MDI prepolymer had an NCO content of 24.5% and was prepared by reacting Rubinol F-456 (a polyether diol available from ICI Americas Inc.) with an 80/20 blend of polymeric MDI to pure MDI. The standard polymeric MDI used was Rubinate M™ and the pure MDI used was Rubinate 44™, both available from ICI Americas Inc. Polyol 1 was "Synperonic T 701" which is an ethylene diamine - based polyol available from ICI Americas Inc.

Formulation A was prepared by blending the components at room temperature in a standard mix cup and stirring by hand.

Southern pine veneers were conditioned to a moisture content of 14.0% in a humid aging cabinet at 95% relative humidity and 35°C (95°F). Formulation A was then applied by brush to one side of two separate veneers at a coating weight of 12.0 g/sq.ft (equivalent to 12.9 mg/cm²). The coated veneers were then brought into contact and pressed

for 20 minutes at room temperature and a pressure of 150 psi (equivalent to 1035 kPa).

The prepared veneers were tested for glue-line formulation according to APA (American Plywood Association) guidelines for exterior type testing. Specifically, each sample veneer was tested for accelerated aging shear. Each sample was boiled for 4 hours and then dried for 20 hours at 62.8 °C (±2.8°C) (145°F (± 5°F)). After drying, the samples were boiled again for 4 hours and cooled in water.

Each sample was then sheared by placing it in a pressure vessel and submerging the entire vessel in cold tap water. A vacuum of 25 inches of mercury (equivalent to 3.4 kPa) was then drawn and maintained for 30 minutes, followed immediately by the application of 65-70 pounds per square inch (equivalent to 449-483 kPa) of pressure for 30 minutes. The samples were then removed from the vessel and tested while wet by tension loading to failure in a shear testing machine. The percentage of wood failure occurring on the sheared surfaces was then estimated for each sample.

The Sample prepared with Formulation A showed a wood failure of greater than 85% at a shear load of 99.0 psi (equivalent to 683 kPa).

Formulation B	Parts By Weight
MDI prepolymer	25.0
Polyol 1	10.0
Thancat DMDEE	0.1
Calcium Carbonate No. 7	10.0

The MDI prepolymer used in Formulation B had an NCO content of 24% and was prepared by reacting Rubinol F-456 with a 60/40 blend of Rubinate M™/Rubinate 44™.

Southern pine veneers were treated as described above with respect to Formulation A, with the exception that the veneers were conditioned to a moisture content of 10%. Formulation B was applied to one side of two separate veneers at a weight of 14 g/sq. ft. (equivalent to 15 mg/cm²). The samples were pressed for 20 minutes at room temperature and 200 psi (equivalent to 1380 kPa).

The samples were tested for accelerated aging shear as described above and were found to have a wood failure of greater than 85% at a shear load 177 psi (equivalent to 1221 kPa).

Formulation C	Parts By Weight
MDI prepolymer	25.0
Polyol 1	3.25
Polyol 2	0.75
NiAx A-4	0.25
Calcium Carbonate No. 7	10.0
SAG 47	0.07

The MDI prepolymer used in Formulation C had an NCO content of 26% and was prepared by reacting Rubinol F-456™ with Rubinate M™. Polyol 2 was "Synperonic T 304" available from ICI Americas Inc. which is also an ethylene-diamine based polyol. SAG 47 is an antifoam agent available from Union Carbide.

Southern pine veneers were conditioned to a moisture content of 10%. Formulation C was applied to one side of two separate veneers at a weight of 12 g/sq. ft. (equivalent to 13 mg/cm²). The system developed cold tack in 10 minutes.

The samples were pre-pressed cold at 150 psi (equivalent to 1035 kPa) for 4 minutes. The samples were then hot-pressed at a temperature of 149°C (300°F) for 3 minutes at 200 psi (equivalent to 1380 kPa).

Each sample was then tested for accelerated aging shear as described above with respect to Formulation A. The samples demonstrated greater than 85% wood failure at a shear load of 92 psi (equivalent to 635 kPa).

Accordingly, it can be seen that the present adhesive compositions provide excellent adhesion as demonstrated by a high degree of wood failure in both cold and hot cure (Formulation C) systems.

Example 2

Eleven resin samples were prepared by mixing Rubinate® 1840 polymeric MDI (PMDI) with a polyol component at room temperature. All samples were prepared by simple hand mixing, although Samples 8-12 required vigorous agitation. The composition of each sample is set forth below in Table 1.

Table 1

1	100% PMDI (control)
2	95% PMDI / 5% Synperonic T 304
3*	97.7% PMDI / 2.26% Daltolac R-140
4	95.7% PMDI / 2.26% Daltolac R-140 / 2.0% Carbowax MOPEGs
5*	99.15% PMDI / 0.85% Vornol R800
6	97.15% PMDI / 0.85% Vornol R800 / 2.0% Carbowax MOPEGs
7	93% PMDI / 7% Synperonic T304
8	95% PMDI / 5% Petrolite X8117
9	95% PMDI / 5% Petrolite X8118
10	95% PMDI / 5% Petrolite X8119
11	95% PMDI / 5% Petrolite X8120
12	95% PMDI / 5% Petrolite X8121

* comparative

Synperonic T304 is an ethylene diamine based polyol with 40% EO from ICI Americas Inc.

Daltolac R-140 is a triethanolamine-based polyol from ICI Americas Inc.

Carbowax MOPEGs is a methoxypolyethylene glycol, available from Union Carbide.

Vornol R800 is a propylene oxide adduct of EDA available from Dow.

Petrolite X-8117 is an oxylated amine having a PO/EO ratio of 80/10 available from Petrolite Corp.

Petrolite X-8118 is an oxylated amine having a PO/EO ratio of 80/30 available from Petrolite Corp.

Petrolite X-8119 is an oxylated amine having a PO/EO ratio of 105/50 available from Petrolite Corp.

Petrolite X-8120 is an oxylated amine having a PO/EO ratio of 105/80 available from Petrolite Corp.

Petrolite X-8121 is an oxylated amine having a PO/EO ratio of 105/90 available from Petrolite Corp.

Ground aspen wafers from Louisiana Pacific were mixed with each resin sample in a ratio of 2:1 wood to resin. Calorimetric measurements were then obtained in a Texas Instruments Differentiated Scanning Colorimeter (DSC) 2910. 30mg samples of the resin/wood mixture were placed in the DSC sample pans and sealed. The samples were heated at a rate of 10°C per minute at 500 psi (equivalent to 3450 kPa). The peak temperature of each sample was measured. The results are set forth in Table 2 with the equivalents of nitrogen per 100g in each sample.

Table 2

Sample	Equivalents of Nitrogen/100g	Peak Temp (°C)
1	0	134
2	0.0061	90
3	0.0061	131
4	0.0061	126
5	0.0061	123
6	0.0061	122
7	0.0084	88
8	0.0001	118
9	0.0008	123
10	0.0006	124
11	0.0005	119
12	0.0005	123

The peak temperature indicates at what point the reaction between the resin and the wood occurs. Therefore, a


lower peak temperature represents high reactivity, i.e., faster cure rate.

As can be seen in Table 2, Samples 2 and 7 have the fastest cure rates. Samples 3 and 5, which contain no ethylene oxide on the polyol, have relatively higher cure rates. Samples 4 and 6, in which the ethylene oxide has been added separately (by the addition of MOPEGs to the system) and thus also do not contain ethylene oxide on the polyol, also have higher cure rates. Samples 8-12 (given as comparative examples) which have a relatively lower amount of amine in the polyol have slower cure rates than those examples having a higher amine concentration.

Accordingly, Example 2 clearly shows that the cure rate improves with an increasing concentration of amine in the polyol and with at least some ethylene oxide on the polyol.

Claims

1. A moisture-activated adhesive composition comprising the reaction product of (a) 99 to 70 % of a polyisocyanate and (b) 1 to 30 % by wt of an isocyanate-reactive component comprising at least one aliphatic tertiary amine group-containing polyol made by alkoxylation of amines or aminoalcohols with at least two active hydrogen atoms with ethylene oxide and optionally propylene oxide, having an ethylene oxide content of at least 1 % and a concentration of nitrogen of 0.002 to 0.02 eqN/100 g.
2. A moisture-activated adhesive composition as in claim 1, further comprising a catalyst.
3. A moisture-activated adhesive composition as in claim 1, wherein said polyisocyanate is a polymeric polyisocyanate.
4. A moisture-activated adhesive composition as in claim 3, wherein said polymeric polyisocyanate is a polymeric diphenylmethane diisocyanate.
5. A moisture-activated adhesive composition as in claim 1, wherein said polyisocyanate is an isocyanate-terminated prepolymer having an NCO content of 10 to 26 %.
6. A moisture-activated adhesive composition as in claim 5, wherein said polyisocyanate is the reaction product of polymeric diphenylmethane diisocyanate and a polyether polyol having a molecular weight of from 1000 to 3000.
7. A moisture-activated adhesive composition as in claim 1, wherein said polyisocyanate is a blend of polymeric diphenylmethane diisocyanate and pure diphenylmethane diisocyanate.
8. A moisture-activated adhesive composition as in claim 1, wherein said aliphatic tertiary amine group-containing polyol has an ethylene oxide content of 1 to 90 %.
9. A moisture-activated adhesive composition as in claim 8, wherein said aliphatic tertiary amine group-containing polyol has an ethylene oxide content of 5 to 60 %.
10. A moisture-activated adhesive composition as in claim 1, wherein said aliphatic tertiary amine group-containing polyol has a molecular weight of 1500 to 10,000 and comprises an initiator having 1 to 18 carbon atoms.
11. A moisture-activated adhesive composition as in claim 1, wherein said aliphatic tertiary amine group-containing polyol is prepared from a compound selected from the group consisting of ethylene diamine, triethylene tetramine and triethanolamine.
12. A moisture-activated adhesive composition as in claim 10, wherein said aliphatic tertiary amine group-containing polyol is an ethylene diamine-based polyol having the following formula:



wherein x is an integer of 1 to 29.0 and y is an integer of 0.1 to 10.

13. A moisture-activated adhesive composition as in claim 2, wherein said catalyst is a tertiary amine catalyst.

14. A process for bonding multiple substrates comprising (1) applying to a surface of a first substrate a moisture-activated adhesive composition as defined in any one of the preceding claims; (2) contacting said surface with a surface of a second substrate; (3) applying pressure to the contacted surfaces; and (4) curing said adhesive composition.

15. A process as in claim 14, wherein said substrate has a moisture content of at least 7 % by weight.

16. A composite article prepared by the process of claim 14.


Patentansprüche

1. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung, umfassend das Reaktionsprodukt von (a) 99 bis 70 Gew.-% eines Polyisocyanats und (b) 1 bis 30 Gew.-% einer isocyanatreaktiven Komponente, welche mindestens ein eine aliphatische tertiäre Aminogruppe enthaltendes Polyol umfaßt, das durch Alkoxylierung von Aminen oder Aminoalkoholen mit mindestens zwei aktiven Wasserstoffatomen mit Ethylenoxid und gegebenenfalls Propylenoxid gemacht wurde, einen Ethylenoxidgehalt von mindestens 1 % und eine Konzentration an Stickstoff von 0,002 bis 0,02 Äquiv. N/100 g hat.
2. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 1, welche weiterhin einen Katalysator umfaßt.
3. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 1, wobei das Polyisocyanat ein polymeres Polyisocyanat ist.
4. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 3, wobei das polymere Polyisocyanat ein polymeres Diphenylmethandiisocyanat ist.
5. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 1, wobei das Polyisocyanat ein isocyanat-terminiertes Vorpolymer mit einem NCO-Gehalt von 10 bis 26 % ist.
6. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 5, wobei das Polyisocyanat das Reaktionsprodukt aus polymerem Diphenylmethandiisocyanat und einem Polyetherpolyol mit einem Molekulargewicht von 1000 bis 3000 ist.
7. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 1, wobei das Polyisocyanat ein Gemisch aus polymerem Diphenylmethandiisocyanat und reinem Diphenylmethandiisocyanat ist.
8. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 1, wobei das eine aliphatische tertiäre Aminogruppe enthaltende Polyol einen Ethylenoxidgehalt von 1 bis 90 % hat.
9. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 8, wobei das eine aliphatische tertiäre Aminogruppe enthaltende Polyol einen Ethylenoxidgehalt von 5 bis 60 % hat.

10. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 1, wobei das eine aliphatische tertiäre Aminogruppe enthaltende Polyol ein Molekulargewicht von 1500 bis 10000 hat und einen Initiator mit 1 bis 18 Kohlenstoffatomen umfaßt.

11. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 1, wobei das eine aliphatische tertiäre Aminogruppe enthaltende Polyol aus einer Verbindung hergestellt wird, die aus der aus Ethylendiamin, Triethylentetramin und Triethanolamin bestehenden Gruppe ausgewählt ist.

12. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 10, wobei das eine aliphatische tertiäre Aminogruppe enthaltende Polyol ein auf Ethylendiamin basierendes Polyol mit der folgenden Formel ist:



wobei x eine ganze Zahl von 1 bis 29,0 und y eine ganze Zahl von 0,1 bis 10 ist.

13. Durch Feuchtigkeit aktivierte Klebstoff-Zusammensetzung nach Anspruch 2, wobei der Katalysator ein tertiärer Amin-Katalysator ist.

14. Verfahren zur Verbindung mehrerer Substrate, umfassend (1) das Auftragen einer durch Feuchtigkeit aktivierten Klebstoffzusammensetzung gemäß einem der vorhergehenden Ansprüche auf eine Oberfläche eines ersten Substrats; (2) das in Kontakt bringen der Oberfläche mit einer Oberfläche eines zweiten Substrats; (3) das Anlegen von Druck an die in Kontakt befindlichen Oberflächen; und (4) das Härten der Klebstoffzusammensetzung.

15. Verfahren nach Anspruch 14, wobei das Substrat einen Feuchtigkeitsgehalt von mindestens 7 Gew.-% hat.

16. Verbundstoff, hergestellt durch das Verfahren gemäß Anspruch 14.

Revendications

1. Composition adhésive activée par l'humidité, comprenant le produit de réaction (a) de 99 à 70 % d'un polyisocyanate et (b) de 1 à 30 % en poids d'un composant réactif vis-à-vis d'un isocyanate, comprenant au moins un polyol aliphatique porteur d'un groupe amino tertiaire, obtenu par alkoxylation d'amines ou d'aminoalcools ayant au moins deux atomes actifs d'hydrogène avec l'oxyde d'éthylène et facultativement l'oxyde de propylène, ayant une teneur en oxyde d'éthylène d'au moins 1 % et une concentration en azote de 0,002 à 0,02 équivalent de N/100 g.

2. Composition adhésive activée par l'humidité suivant la revendication 1, comprenant en outre un catalyseur.

3. Composition adhésive activée par l'humidité suivant la revendication 1, dans laquelle le polyisocyanate est un polyisocyanate polymère.

4. Composition adhésive activée par l'humidité suivant la revendication 3, dans laquelle le polyisocyanate polymère est un diisocyanatodiphénylméthane polymère.


5. Composition adhésive activée par l'humidité suivant la revendication 1, dans laquelle le polyisocyanate est un prépolymère à terminaison isocyanate et ayant une teneur en NCO de 10 à 26 %.

6. Composition adhésive activée par l'humidité suivant la revendication 5, dans laquelle le polyisocyanate est le produit de réaction de diisocyanatodiphénylméthane polymère et d'un polyétherpolyol ayant un poids moléculaire de 1000 à 3000.

7. Composition adhésive activée par l'humidité suivant la revendication 1, dans laquelle le polyisocyanate est un

mélange de diisocyanatodiphénylméthane polymère et de diisocyanatodiphénylméthane pur.

8. Composition adhésive activée par l'humidité suivant la revendication 1, dans laquelle le polyol aliphatique contenant un groupe amino tertiaire a une teneur en oxyde d'éthylène de 1 à 90 %.
9. Composition adhésive activée par l'humidité suivant la revendication 8, dans laquelle le polyol aliphatique contenant un groupe amino tertiaire a une teneur en oxyde d'éthylène de 5 à 60 %.
10. Composition adhésive activée par l'humidité suivant la revendication 1, dans laquelle le polyol aliphatique contenant un groupe amino tertiaire a un poids moléculaire de 1500 à 10 000 et comprend un initiateur ayant 1 à 18 atomes de carbone.
11. Composition adhésive activée par l'humidité suivant la revendication 1, dans laquelle le polyol aliphatique contenant un groupe amino tertiaire est préparé à partir d'un composé choisi dans le groupe consistant en l'éthylènediamine, la triéthylènetétramine et la triéthanolamine.
12. Composition adhésive activée par l'humidité suivant la revendication 10, dans laquelle le polyol aliphatique contenant un groupe amino tertiaire est un polyol à base d'éthylènediamine répondant à la formule suivante :



dans laquelle x est un nombre entier de 1 à 29,0 et y est un nombre entier de 0,1 à 10.

13. Composition adhésive activée par l'humidité suivant la revendication 2, dans laquelle le catalyseur est un catalyseur à base d'amine tertiaire.
14. Procédé de liaison de substrats multiples, comprenant (1) l'application à une surface d'un premier substrat d'une composition adhésive activée par l'humidité telle que définie dans l'une quelconque des revendications précédentes ; (2) la mise en contact de cette surface avec une surface d'un second substrat ; (3) l'application d'une pression aux surfaces en contact ; et (4) le durcissement de la composition adhésive.
15. Procédé suivant la revendication 14, dans lequel le substrat a une teneur en humidité d'au moins 7 % en poids.
16. Article composite produit par un procédé suivant la revendication 14.